

Amroy CA35 – Curing agent for epoxies

- ✓ **Fast cure Low viscosity liquid curing agent**
- ✓ **Suitable for all reinforcement structures**
- ✓ **Use with high performance HYBTONITE® nanoepoxy resin**
- ✓ **Compatible with most industrial processes**

Amroy CA35 cycloaliphatic amine

The curing agent is a tailor-made low viscosity amine curing agent.

It is suitable for many industrial applications including infusion, RTM, laminating etc. It imparts

excellent wetting and mechanical performance with HYBTONITE® resin.

Amroy CA35 – curing agent for Epopox™, Hybtonite® and Firetonite™ epoxies

Description	Amine blend
Ahew (Calc.), g/equiv.	59 – 61
Viscosity, mPa·S	5 – 20
Gel time min at 21 °C	240 – 500
Min cure temperature, °C	25
Tensile Modulus, GPa	3 - 4 GPa (Depends heavily on resin and cure schedule)
Max Elongation at break, %	8-12 (Depends on resin)
Optimal cure schedule	4 hours 60 °C + 4 hours 80 °C (Can be taylor made)
Max Tg w. heat cure, °C	100
Properties	Good wetting, easy to operate; Tg less than 100 °C, long pot life

Storage life

The system does not crystallize. Storage time is at least three years in closed containers stored at 5 – 40 °C protected from direct sunlight and water..

Amroy Europe Oy

VAT No: FI19869654

Postal address
Fax
Homepage

P. O. Box 144, FI – 15101 Lahti, FINLAND
+358 20 711 8609 (production & orders)
www.amroy.fi

All this information is given in good faith and is based on Amroy Europe Oy's and its partners' investigations and knowledge. Amroy Europe Oy does not guarantee any of this data nor the misuse of this product or its consequences because the conditions of use are beyond our control. Furthermore nothing contained here shall be construed in conflict with any patents.